

Evaluation of Critical Quality Control Tests for Natural Rubber and Latex Conformance: Methods, Calculations, and Industrial Significance

Ojisua, O.K ¹, Uwague, E.E ¹, Dauda, M.O ¹, Anokwuru, S.N ¹, Odidi, D.O ¹

¹Rubber Research Institute of Nigeria, P.M.B. 1049, Benin City, Edo State, Nigeria

E-mail: uncledee4life2017@gmail.com

ARTICLE INFO


Keywords:

Natural rubber,
latex concentrate,
quality control,
dry rubber content,
KOH number,
mechanical stability time,
plasticity retention index,
ISO 2004,
ISO 2000,
conformance testing.

Vol.01, No.03, 2026

Copyright © 2026 by author(s) and Scientific Research Publishing Inc. This work is licensed under the Creative Commons Attribution International License (CCBY4.0).

<http://creativecommons.org/licenses/by/4.0/>



ABSTRACT

Natural rubber (NR) and natural rubber latex concentrate are biologically derived raw materials whose composition varies with clone, tapping regime, season, coagulation practice, and storage history. Because downstream vulcanisate performance is highly sensitive to this variability, conformance assessment relies on a defined battery of standardised laboratory tests rather than on a single index. This paper evaluates the critical quality control tests applied to ammonia-preserved latex concentrate and to technically specified dry rubber, presenting for each test its principle, procedure, governing standard, computational basis, and interpretive significance for processing and product performance. Tests examined for latex concentrate include total solids content (ISO 124), dry rubber content (ISO 126), alkalinity (ISO 125), KOH number (ISO 127), volatile fatty acid number (ISO 506), mechanical stability time (ISO 35), coagulum content (ISO 706), and sludge content (ISO 2005), assessed against the specification limits of ISO 2004 and ASTM D1076. Tests examined for dry rubber include dirt retained on a 45 µm sieve (ISO 249), ash (ISO 247), nitrogen (ISO 1656), volatile matter (ISO 248), initial Wallace plasticity (ISO 2007), plasticity retention index (ISO 2930), and Mooney viscosity (ISO 289), assessed against ISO 2000. Calculation formulae are given explicitly with worked numerical illustrations. Sources of measurement variability, repeatability and reproducibility considerations under ISO 5725, and laboratory competence requirements under ISO/IEC 17025 are discussed. The evaluation concludes that no single parameter is sufficient for conformance decisions, that colloidal-stability indices and plasticity indices carry the greatest predictive weight for processing outcomes, and that disciplined sampling and sample conditioning frequently dominate the total uncertainty budget.

Introduction

Natural rubber is obtained as a colloidal aqueous dispersion, field latex, tapped from *Hevea brasiliensis*. Fresh field latex typically contains 30 to 40 per cent (m/m) rubber hydrocarbon, together with proteins, lipids, phospholipids, carbohydrates, inorganic salts, and water. The rubber phase consists of cis-1,4-polyisoprene particles stabilised by an adsorbed layer of proteins and phospholipids that confers a net negative surface charge and thus electrostatic and steric stability. Because this stabilising layer is biological in origin, it is susceptible to enzymatic and microbial degradation, and the colloidal system is therefore metastable rather than indefinitely stable.

Two principal commercial forms are derived from field latex. The first is latex concentrate, produced by centrifugation or creaming to approximately 60 per cent dry rubber content and preserved with ammonia, alone or in combination with secondary preservatives such as tetramethylthiuram disulfide and zinc oxide. Latex concentrate is the feedstock for dipped goods including examination and surgical gloves, catheters, and condoms, and for foam, adhesives, and thread. The second is dry rubber, produced by acid coagulation of field latex or by processing of field coagula, followed by comminution, washing, drying, and baling. Dry rubber is the feedstock for tyres, technical mouldings, conveyor belting, and engineering components.

The commercial and technical problem addressed by quality control testing is that raw material variability propagates directly into processing behaviour and end-product performance. Latex

concentrate with marginal colloidal stability may flocculate in pipework, pumps, or dipping tanks, causing line stoppage and product defects. Latex with elevated non-rubber solids may exhibit altered film-forming behaviour and modified tensile properties after vulcanisation. Dry rubber with excessive dirt introduces stress-concentrating inclusions that reduce fatigue life. Rubber with low plasticity retention oxidises rapidly during mixing and storage, producing inconsistent viscosity and unpredictable processing. Because these consequences are costly and are frequently detected only after substantial value has been added, conformance is assessed on the raw material rather than inferred from finished product performance.

Conformance assessment is codified in international and national specification standards. For ammonia-preserved latex concentrate, ISO 2004 and ASTM D1076 define grade classes and numerical limits. For technically specified rubber, ISO 2000 defines the grading scheme in which the numeric suffix corresponds principally to the maximum permissible dirt content, and national schemes including Standard Malaysian Rubber, Standard Indonesian Rubber, Thai Standard Rubber, and Standard Vietnamese Rubber implement broadly congruent requirements. These specification standards reference separate test method standards that define the procedures by which each parameter is determined.

The purpose of this paper is to evaluate the critical tests in this battery on three dimensions. First, the measurement principle and procedure of each test are described with sufficient specificity to make the sources of variability apparent. Second, the calculation basis is given explicitly, since several parameters in this field are expressed on unusual bases, notably per 100 grams of total solids rather than per 100 grams of sample, and misapplication of the basis is a recurrent source of reported error. Third, the industrial significance of each parameter is assessed, distinguishing tests that directly predict processing behaviour from those that principally serve as contamination or adulteration indicators. The paper is a methodological and interpretive evaluation; it does not report new experimental data.

2. Background

2.1 Colloidal structure of natural rubber latex

The stability of natural rubber latex derives from the composite interfacial layer surrounding each rubber particle. Proteins adsorbed at the particle surface ionise at the alkaline pH maintained by ammonia preservation, generating negative charge and electrostatic repulsion described by Derjaguin-Landau-Verwey-Overbeek theory. Phospholipids, principally phosphatidylcholine and phosphatidylethanolamine species, contribute additional steric stabilisation and are chemically linked to the polyisoprene chain ends in a proportion of particles, giving rise to the branching and gel content characteristic of natural rubber.

Ammonia serves three distinct preservative functions that are frequently conflated. It raises pH, increasing protein ionisation and hence electrostatic stabilisation. It acts as a bacteriostat, suppressing the microbial population that would otherwise metabolise carbohydrates and non-rubber constituents to volatile fatty acids. It hydrolyses phospholipids over time, liberating higher fatty acids that form ammonium soaps; these soaps are themselves surfactants and contribute to long-term stabilisation, but their accumulation is measurable as an increase in KOH number. The maturation behaviour of latex concentrate during storage is largely the resultant of these competing processes.

2.2 Degradation pathways and their measurable signatures

Two degradation pathways dominate and are separately detectable. Microbial degradation produces volatile fatty acids, principally acetic, propionic, formic, and butyric acids, from carbohydrate and non-rubber substrates. These acids consume ammonia as ammonium salts, lowering effective alkalinity and destabilising the system. Their concentration is quantified by the volatile fatty acid number determined under ISO 506, which is regarded as the most direct indicator of bacterial spoilage and of the adequacy of preservation practice from tapping through to receipt.

Chemical hydrolysis of phospholipids liberates higher fatty acids that are non-volatile under the conditions of the VFA determination. These acids, together with any volatile acids present, are quantified collectively by the KOH number determined under ISO 127. A high KOH number is therefore ambiguous in isolation: it may reflect benign maturation through phospholipid hydrolysis, or it may reflect bacterial spoilage. Interpretation requires the VFA number in parallel, and the pairing of the two determinations is diagnostically more informative than either alone.

2.3 Structure-property relationships in dry natural rubber

Natural rubber exhibits a broad molecular mass distribution, typically with weight-average molecular mass in the range of 1×10^6 to 2.5×10^6 g/mol, together with a gel fraction arising from chain-end branching and from crosslinking through abnormal groups. Storage hardening, the spontaneous increase in viscosity during storage, proceeds through reaction of aldehyde groups on the polyisoprene chain with proteins and amino acids, and is suppressed in constant-viscosity grades by treatment with hydroxylamine salts that block the aldehyde functionality.

Oxidative degradation proceeds through hydroperoxide formation at the α -methylenic positions adjacent to the double bond, followed by chain scission. Natural rubber contains endogenous antioxidants including tocotrienols and certain amino acids, whose concentration varies with clone and processing history. The plasticity retention index provides an empirical measure of resistance to this oxidative chain scission and correlates in practice with mixing behaviour, viscosity stability, and processing consistency.

2.4 Specification frameworks

ISO 2004 classifies centrifuged and creamed ammonia-preserved latex concentrate into types distinguished principally by preservative system and alkalinity. Type HA is preserved with ammonia alone and requires alkalinity of at least 0.60 per cent (m/m) calculated on the latex. Type LA is preserved with ammonia together with secondary preservatives and requires alkalinity not exceeding 0.29 per cent (m/m). Type XA, preserved with ammonia together with other preservatives, requires alkalinity of at least 0.30 per cent (m/m). ASTM D1076 defines broadly comparable categories with some differences in limit values and in the specific tests required.

ISO 2000 specifies technically specified rubber in grades whose numeric designation corresponds principally to the dirt limit. Grade TSR 10 permits dirt retained on a 45 μ m sieve of at most 0.10 per cent (m/m); TSR 20 permits at most 0.20 per cent. Ash limits are 0.75 per cent for TSR 10 and 1.00 per cent for TSR 20. Nitrogen is limited to 0.60 per cent and volatile matter to 0.80 per cent across the common grades. Plasticity retention index minima decrease with grade number, reflecting the poorer field material used for higher-numbered grades. Constant-viscosity and light-colour grades carry additional requirements on Mooney viscosity and on Lovibond colour index respectively.

3. Test Methods, Procedures and Calculations

3.1 Sampling and sample preparation

Sampling is the most frequently underestimated contributor to total measurement uncertainty in this field. Latex concentrate stratifies during storage, with a cream layer of higher rubber content forming at the upper surface and a sludge layer of higher density material settling at the base. Sampling from a single depth therefore yields an unrepresentative specimen. ISO 123 specifies sampling procedures requiring either thorough homogenisation of the container before sampling or the use of a sampling tube that draws a full-depth core. For bulk tanks and road tankers, composite sampling from multiple depths and positions is required.

Dry rubber presents an analogous problem at a different scale. A bale is heterogeneous because it is formed from many individual crumb particles of differing origin and because the drying process produces a moisture and oxidation gradient from surface to core. ISO 1795 specifies sampling of bales, requiring that test portions be taken from a defined depth below the bale surface to avoid the oxidised and moisture-depleted surface layer. Test portions are homogenised by passing through a laboratory two-roll mill under specified conditions before those tests, such as plasticity determination, that are sensitive to prior mechanical and thermal history.

Sample conditioning is specified for tests whose result is temperature or humidity dependent. Plasticity determinations under ISO 2007 require conditioning at the standard laboratory temperature of 23 ± 2 °C, and the plastimeter platens are controlled at 100 ± 1 °C. Failure to condition adequately produces systematic bias in the initial plasticity value and hence in the derived plasticity retention index.

3.2 Total solids content (ISO 124)

Total solids content quantifies all non-volatile material in the latex, comprising rubber hydrocarbon together with non-rubber solids. A test portion of approximately 2.5 g is weighed to 0.1 mg into a flat-bottomed dish, spread evenly, and dried in an oven at 70 ± 2 °C until constant mass is attained, with constant mass defined as successive weighings after further drying periods differing by not more

than 1 mg. Drying at higher temperatures is not permitted because it causes surface skin formation that traps water and produces a falsely low result.

The calculation is: $TSC (\%) = (m_2 / m_1) \times 100$, where m_1 is the mass of the test portion and m_2 is the mass of the dried residue. As a worked illustration, a test portion of 2.4128 g yielding a dried residue of 1.4863 g gives $TSC = (1.4863 / 2.4128) \times 100 = 61.60$ per cent. ISO 2004 requires a minimum of 61.5 per cent for centrifuged concentrate of the principal types, so this result conforms with minimal margin.

3.3 Dry rubber content (ISO 126)

Dry rubber content quantifies the rubber hydrocarbon fraction specifically and is the parameter on which latex concentrate is normally traded, since it determines the yield of rubber available for product formation. A test portion of approximately 10 g is diluted, coagulated by controlled addition of dilute acetic acid, and the coagulum is formed into a thin sheet, washed thoroughly in running water to remove serum constituents, and dried at $70 \pm 2^\circ\text{C}$ to constant mass.

The calculation is: $DRC (\%) = (m_3 / m_1) \times 100$, where m_1 is the mass of the test portion and m_3 is the mass of the washed, dried coagulum. Continuing the worked example, a test portion of 10.0214 g yielding washed dried coagulum of 6.0329 g gives $DRC = (6.0329 / 10.0214) \times 100 = 60.20$ per cent, which conforms to the ISO 2004 minimum of 60.0 per cent.

The critical procedural variables are the completeness of coagulation, which depends on acid addition rate and final pH, and the thoroughness of washing, which determines how much serum solid remains occluded in the coagulum. Incomplete washing biases DRC upward and correspondingly biases the derived non-rubber solids downward. Sheet thickness must be controlled because thick sheets cannot be washed effectively and dry unevenly.

3.4 Non-rubber solids

Non-rubber solids are not determined directly but are obtained by difference: $NRS (\%) = TSC (\%) - DRC (\%)$. From the worked values above, $NRS = 61.60 - 60.20 = 1.40$ per cent, conforming to the ISO 2004 limit of 2.0 per cent maximum. Because NRS is a difference of two independently determined quantities of similar magnitude, its relative uncertainty is substantially larger than that of either component. If TSC and DRC each carry a standard uncertainty of 0.05 per cent, the combined standard uncertainty on NRS is approximately 0.07 per cent, which represents 5 per cent of a nominal 1.40 per cent value. This error propagation is frequently overlooked when NRS results near the specification limit are disputed.

Elevated non-rubber solids indicate either inefficient centrifugation, leaving serum constituents in the concentrate, or the presence of added non-rubber material. The parameter is therefore both a process-efficiency indicator and an adulteration indicator, and it has direct technical significance because serum proteins and carbohydrates affect film formation, water absorption of the vulcanisate, and, in the case of extractable proteins, the allergenic potential of dipped products.

3.5 Alkalinity (ISO 125)

Alkalinity is determined by titration of a diluted test portion with standard hydrochloric acid to a defined end point, using either an indicator or potentiometric detection. It is conventionally expressed as ammonia, whether or not all alkalinity is attributable to ammonia. The calculation on a latex basis is: $\text{Alkalinity (\% m/m as NH}_3\text{)} = (V \times c \times 0.01703 \times 100) / m$, where V is the volume of hydrochloric acid in millilitres, c is its concentration in mol/L, 0.01703 is the molar mass of ammonia in kg/mol expressed for consistency of units, and m is the mass of the test portion in grams.

As an illustration, a test portion of 5.0132 g requiring 18.42 mL of 0.1000 mol/L hydrochloric acid gives $\text{alkalinity} = (18.42 \times 0.1000 \times 0.01703 \times 100) / 5.0132 = 0.626$ per cent, conforming to the type HA minimum of 0.60 per cent. Alkalinity may alternatively be expressed on the aqueous phase, in which case the latex-basis value is divided by the water fraction; the basis must be stated explicitly because the two values differ by a factor of approximately 2.5 at typical concentrate solids.

Alkalinity is the primary control parameter for colloidal stability and for bacteriostasis. It declines during storage as ammonia volatilises and as it is consumed by neutralisation of accumulating acids. Consignments received with alkalinity near the lower limit warrant either prompt use or ammonia adjustment, and a downward trend across successive deliveries from one supplier indicates a preservation practice problem upstream.

3.6 KOH number (ISO 127)

The KOH number is defined as the number of grams of potassium hydroxide equivalent to the acid radicals combined with ammonia in a sample of latex containing 100 g of total solids. The determination involves potentiometric titration of a test portion, previously adjusted for free ammonia, with standard potassium hydroxide solution to a defined end point in the region of pH 10.5, the inflection corresponding to neutralisation of the ammonium salts of the combined acids.

The calculation is: $\text{KOH number} = (V \times c \times 56.11 \times 100) / (m \times \text{TSC})$, where V is the volume of potassium hydroxide solution in millilitres, c is its concentration in mol/L, 56.11 g/mol is the molar mass of potassium hydroxide, m is the mass of the test portion in grams, and TSC is the total solids content in per cent. As an illustration, a test portion of 50.24 g of latex of TSC 61.60 per cent requiring 5.86 mL of 0.500 mol/L potassium hydroxide gives $\text{KOH number} = (5.86 \times 0.500 \times 56.11 \times 100) / (50.24 \times 61.60) = 0.531$. ISO 2004 specifies a maximum of 0.80 for the principal types.

The KOH number rises during storage through both phospholipid hydrolysis and bacterial acid production. Because it aggregates both contributions, a rising KOH number requires interpretation alongside the volatile fatty acid number. A high KOH number with a low VFA number indicates advanced but benign chemical maturation, and such latex is typically well stabilised though it may exhibit altered thickening response to compounding. A high KOH number accompanied by a high VFA number indicates spoilage and predicts poor mechanical stability and increased flocculation risk in processing.

3.7 Volatile fatty acid number (ISO 506)

The volatile fatty acid number is defined as the number of grams of potassium hydroxide required to neutralise the volatile fatty acids in a sample of latex containing 100 g of total solids. The determination proceeds by coagulating a diluted test portion with ammonium sulfate solution, filtering to obtain a clear serum, acidifying the serum with sulfuric acid, and steam-distilling the liberated volatile acids into a receiver. The distillate is titrated with standard barium hydroxide or sodium hydroxide solution.

The calculation follows the same structural form as the KOH number: $\text{VFA number} = (V \times c \times 56.11 \times 100 \times f) / (m \times \text{TSC})$, where f is the distillation recovery factor determined by calibration of the apparatus with a standard acid, and the remaining symbols are as previously defined. The recovery factor is essential because steam distillation of volatile acids is incomplete under practical conditions and the recovery is apparatus-dependent. Failure to determine and apply a current recovery factor is a common source of systematic error between laboratories.

The VFA number is the most direct available indicator of bacterial activity in the latex. Values below approximately 0.05 indicate well-preserved material; values approaching or exceeding 0.20 indicate substantial spoilage and are associated with reduced mechanical stability and with odour that may be objectionable in the manufacturing environment. Because volatile acids can form rapidly under warm conditions with inadequate preservation, the VFA number is particularly informative for material subject to extended transit or to interruption of the cold chain where one is maintained.

3.8 Mechanical stability time (ISO 35)

Mechanical stability time is a direct empirical measure of resistance to shear-induced flocculation and is the single test most predictive of behaviour in pumps, pipework, agitated tanks, and dipping lines. A test portion is adjusted to 55.0 ± 0.2 per cent total solids, brought to 35 ± 1 °C, and subjected to high-speed agitation at $14\,000 \pm 200$ rev/min using a specified disc in a specified vessel geometry. The elapsed time to the first appearance of flocculation, detected by drawing a drop across a glass surface at intervals, is recorded in seconds.

No calculation is required beyond reporting the elapsed time, but the adjustment to standard solids is essential and is itself a source of error, since mechanical stability is strongly dependent on solids content. ISO 2004 specifies a minimum of 650 s for the principal types. Values substantially above the minimum, in the range of 900 to 1400 s, are typical of well-matured concentrate and are generally preferred by dipped-goods manufacturers. Very high values, above approximately 1800 s, may indicate over-stabilisation that can impede the controlled destabilisation required in coagulant dipping.

Mechanical stability time increases during the first weeks of storage as ammonium soaps accumulate, then plateaus, and declines if spoilage proceeds. The characteristic maturation curve means

that freshly produced concentrate may fail the specification while the same material passes after two to three weeks of storage; specification testing timing must therefore be defined contractually.

3.9 Coagulum and sludge content (ISO 706, ISO 2005)

Coagulum content quantifies pre-formed coagulated rubber that would foul filters, blind screens, and produce inclusion defects in thin-walled dipped products. A weighed test portion is diluted and passed through a 180 µm sieve; the retained material is washed, dried, and weighed. The calculation is: $\text{Coagulum (\%)} = (m_c / m_i) \times 100$. ISO 2004 specifies a maximum of 0.05 per cent for the principal types, a demanding limit reflecting the acute sensitivity of thin-film products to particulate inclusions.

Sludge content quantifies dense non-rubber material, principally magnesium ammonium phosphate together with soil-derived mineral matter, which settles during storage. A test portion is centrifuged under specified conditions and the deposit is washed, dried, and weighed. The calculation follows the same form. ISO 2004 specifies a maximum of 0.10 per cent. Elevated sludge indicates either inadequate field latex sieving and settling before centrifugation, or high magnesium content in the field latex, which is clone- and soil-dependent and which may be managed by addition of diammonium hydrogen phosphate before concentration.

3.10 Dirt content of dry rubber (ISO 249)

Dirt content is the defining parameter of the technically specified rubber grading scheme. A test portion of approximately 10 g is dissolved in a specified solvent, typically a high-boiling mineral oil or a solvent blend, under controlled heating with a peptising agent to break down gel. The resulting solution is filtered through a 45 µm aperture sieve, and the retained residue is washed with solvent, dried, and weighed.

The calculation is: $\text{Dirt (\%)} = (m_d / m_i) \times 100$, where m_d is the mass of dried residue on the sieve. As an illustration, a test portion of 10.0087 g leaving 0.0071 g of retained residue gives $\text{Dirt} = (0.0071 / 10.0087) \times 100 = 0.071$ per cent, which conforms to the TSR 10 limit of 0.10 per cent but not to the TSR 5 limit of 0.05 per cent. Because the retained masses are small, weighing precision and the completeness of solvent removal before weighing are critical, and blank determinations are required.

Dirt consists principally of soil, sand, and bark fragments introduced during tapping, collection, and field coagulation. Its technical significance lies in the role of hard inclusions as stress concentrators that initiate fatigue cracks, which is why dirt limits are most stringent for grades intended for dynamically loaded applications. Dirt content is essentially a measure of field hygiene and cannot be corrected by later processing except through more aggressive washing, which carries its own cost and effluent penalty.

3.11 Ash content (ISO 247)

Ash content quantifies the inorganic residue remaining after complete combustion of the organic fraction. A test portion of approximately 5 g is charred and then ignited in a muffle furnace at 550 ± 25 °C to constant mass. The calculation is: $\text{Ash (\%)} = (m_a / m_i) \times 100$. ISO 2000 specifies maxima of 0.75 per cent for TSR 10 and 1.00 per cent for TSR 20.

Ash arises from three sources that the test does not distinguish: endogenous mineral constituents of the latex, principally potassium, magnesium, phosphorus, and calcium; soil contamination, which also contributes to dirt; and residues of processing chemicals. Elevated ash with normal dirt suggests either high endogenous mineral content or soluble chemical residue, whereas elevated ash accompanied by elevated dirt indicates soil contamination. The parameter is therefore most informative when read jointly with dirt.

3.12 Nitrogen content (ISO 1656)

Nitrogen content serves as a proxy for protein content, applying the conventional assumption that rubber-associated protein contains approximately 16 per cent nitrogen. Determination is by the Kjeldahl method: the test portion is digested in concentrated sulfuric acid with a catalyst to convert organic nitrogen to ammonium sulfate, the digest is made alkaline, and the liberated ammonia is distilled into boric acid and titrated with standard acid.

The calculation is: $\text{Nitrogen (\%)} = (V \times c \times 14.007 \times 100) / (m \times 1000)$, where V is the titre volume in millilitres, c is the acid concentration in mol/L, 14.007 g/mol is the atomic mass of nitrogen, and m is the test portion mass in grams. As an illustration, a test portion of 1.0043 g requiring 3.24 mL of 0.0100

mol/L acid gives Nitrogen = $(3.24 \times 0.0100 \times 14.007 \times 100) / (1.0043 \times 1000) = 0.452$ per cent, conforming to the ISO 2000 limit of 0.60 per cent.

Protein content influences several properties of practical significance. It accelerates cure, since amino compounds act as accelerator activators, so variation in nitrogen content produces variation in cure rate that is troublesome in continuous processes. It increases water absorption of the vulcanisate. In latex products it is associated with extractable protein and hence with Type I allergenic potential, though the relationship between total nitrogen and extractable allergenic protein is indirect and the latter is assessed by dedicated immunoassay methods rather than by Kjeldahl nitrogen.

3.13 Volatile matter (ISO 248)

Volatile matter is principally residual moisture together with any volatile organic residues. It is determined either by oven drying at 100 ± 5 °C to constant mass or by hot-mill drying, in which the test portion is passed through a two-roll mill at defined temperature and nip. The calculation is: Volatile matter (%) = $((m_1 - m_2) / m_1) \times 100$. ISO 2000 specifies a maximum of 0.80 per cent.

Excessive volatile matter causes porosity in extrudates and mouldings, promotes mould fouling, and, in bales, permits microbial growth and mould development during storage. It also biases all other results reported on a mass basis, since it dilutes the material; where volatile matter is near the limit, some purchasers require other parameters to be reported on a dry basis for comparability.

3.14 Wallace plasticity and plasticity retention index (ISO 2007, ISO 2930)

The Wallace rapid plastimeter compresses a cylindrical test piece of defined volume between parallel platens at 100 ± 1 °C, first to a preheat thickness for 15 s and then under a standard load of 100 N for 15 s, reporting the final thickness in units of 0.01 mm as the plasticity number. The initial plasticity, designated P_0 , is determined on the conditioned test piece. ISO 2000 specifies a minimum P_0 of 30 for several grades.

The plasticity retention index is the central oxidative-stability parameter for dry natural rubber. Duplicate test pieces are aged in a circulating-air oven at 140 ± 0.2 °C for exactly 30 min, then cooled and tested to obtain the aged plasticity P_{30} . The index is calculated as: $PRI = (P_{30} / P_0) \times 100$. As an illustration, $P_0 = 38$ and $P_{30} = 26$ give $PRI = (26 / 38) \times 100 = 68$, conforming to the TSR 10 minimum of 50 and to the TSR 5 minimum of 60.

The determination is unusually sensitive to procedural detail. Oven temperature uniformity is critical because the ageing reaction rate is strongly temperature dependent; the tolerance of ± 0.2 °C is among the tightest in rubber testing and requires a mapped and regularly verified oven. Ageing time must be controlled to a few seconds. Test pieces must be positioned to receive uniform air flow, and oven loading affects recovery time after door opening. Interlaboratory disagreement on PRI is common and is most often traced to oven performance rather than to the plastimeter.

Low PRI indicates rubber that will degrade rapidly under the thermal and shear conditions of mixing, producing lower and less predictable compound viscosity, altered filler dispersion, and reduced vulcanisate fatigue performance. High PRI is associated with consistent processing. Because PRI is sensitive to both endogenous antioxidant content and to prior oxidative history, it captures information about both raw material quality and processing and storage conditions that no single compositional parameter provides.

3.15 Mooney viscosity (ISO 289)

Mooney viscosity is measured in a shearing-disc viscometer in which a serrated rotor embedded in the test piece is rotated at 2 rev/min within a closed, heated die cavity. The standard determination for natural rubber is ML(1+4) at 100 °C, denoting a large rotor, one minute preheat, and reading taken four minutes after rotor start. The value is reported in arbitrary Mooney units without further calculation.

Mooney viscosity is the principal specification parameter for constant-viscosity grades, which are produced with hydroxylamine treatment to arrest storage hardening and are typically specified at nominal 50 or 60 Mooney units with a defined tolerance. For non-constant-viscosity grades, Mooney viscosity is informative but drifts upward during storage, so the value must be interpreted together with the age of the material. Viscosity governs mixing energy, mill and extruder behaviour, and die swell, and is therefore the parameter most directly relevant to factory throughput.

4. Comparative Evaluation

4.1 Diagnostic value and redundancy among latex tests

The latex test battery contains both complementary and partially redundant elements. Total solids content and dry rubber content are individually necessary because the first governs drying and film-forming behaviour while the second determines rubber yield, and their difference yields the non-rubber solids that neither provides alone. Alkalinity, KOH number, and volatile fatty acid number together describe the preservation state, but they are not interchangeable: alkalinity measures current buffering capacity, the KOH number measures accumulated combined acid from all sources, and the VFA number isolates the bacterial contribution. Mechanical stability time integrates the effects of all of these into a single functional response and is the closest available laboratory analogue of processing behaviour.

Where testing capacity is constrained, the diagnostic yield per test is highest for mechanical stability time, volatile fatty acid number, and dry rubber content. Mechanical stability time predicts the failure mode of greatest operational cost; the VFA number identifies the degradation pathway that is both most damaging and most amenable to upstream correction; and dry rubber content determines the commercial basis of the transaction. Coagulum and sludge content are essential for thin-film applications but carry less information for bulk applications such as adhesives and foam.

4.2 Diagnostic value and redundancy among dry rubber tests

Among dry rubber tests, plasticity retention index carries the greatest predictive weight for processing consistency, and initial plasticity or Mooney viscosity carries the greatest weight for mixing and forming behaviour. Dirt content is the defining grading parameter and directly predicts fatigue-critical defect density. Ash, nitrogen, and volatile matter are individually less predictive of processing outcomes but serve important roles as contamination and process-control indicators, and their joint pattern is informative in ways that individual values are not, as noted for the ash-dirt relationship.

A recurrent practical question is whether Mooney viscosity can substitute for Wallace plasticity. The two correlate but imperfectly, because they probe different deformation regimes and are differently sensitive to gel content. Specifications that permit either measurement without a defined conversion invite dispute. Where both are available, the pair is more informative than either, since divergence between them frequently indicates unusual gel content or molecular mass distribution.

4.3 Measurement uncertainty and interlaboratory agreement

Repeatability and reproducibility for these methods, expressed in the framework of ISO 5725, differ substantially across the battery. Gravimetric determinations conducted with adequate balance performance and thorough drying, notably total solids content and dry rubber content, typically achieve repeatability standard deviations below 0.1 per cent absolute. Titrimetric determinations are similarly well controlled provided that titrant standardisation is current and end-point detection is potentiometric rather than visual.

By contrast, the plasticity retention index and the mechanical stability time exhibit substantially poorer reproducibility. For PRI, the dominant contributor is ageing oven performance, including temperature uniformity across the working volume, recovery after door opening, and air circulation rate. For mechanical stability time, the dominant contributors are the accuracy of solids adjustment, the condition and dimensional conformity of the stirrer disc, and the subjectivity of flocculation end-point detection. Laboratories reporting these parameters should participate in proficiency testing schemes and should treat marginal results near specification limits with explicit acknowledgement of uncertainty rather than as sharp pass or fail determinations.

Where sampling is included in the uncertainty budget, it frequently dominates. For a stratified latex tank sampled from a single depth, the sampling contribution to dry rubber content uncertainty can exceed the analytical contribution by an order of magnitude. Investment in sampling discipline therefore yields greater improvement in total measurement quality than investment in analytical refinement, a conclusion that runs counter to the usual allocation of laboratory improvement effort.

4.4 Laboratory competence and conformity assessment

Testing laboratories operating in a conformity assessment role are commonly accredited to ISO/IEC 17025, which requires demonstrated technical competence, method validation or verification, metrological traceability of measurement results, participation in proficiency testing, and a defined approach to reporting conformity statements in the presence of measurement uncertainty. The last requirement is directly relevant to the marginal-result problem identified above: a decision rule must be

defined and stated, specifying whether a result falling within the uncertainty interval around a specification limit is reported as conforming, non-conforming, or indeterminate.

Traceability requirements bear on several tests. Balances require calibration with weights traceable to national standards. Titrant solutions require standardisation against certified primary standards. Temperature-controlled equipment, in particular the PRI ageing oven and the plastimeter platens, requires calibration with traceable temperature standards and, for the oven, spatial mapping of the working volume. Sieves used for dirt and coagulum determination require verification of aperture conformity, since sieve wear increases effective aperture and biases results low.

4.5 Instrumental and rapid alternatives

Several instrumental techniques have been evaluated as rapid alternatives or supplements to the classical battery. Near-infrared spectroscopy has been applied to simultaneous estimation of total solids and dry rubber content in latex, offering results in seconds without sample destruction, at the cost of requiring calibration against reference methods on a matrix-matched sample set and periodic recalibration as material sources change. Microwave and radiofrequency moisture analysers offer rapid volatile matter determination for dry rubber. Rubber process analysers and moving-die rheometers characterise cure behaviour more informatively than any of the specification parameters, though they are not part of the ISO 2000 grading scheme.

These techniques are best positioned as process control tools operating alongside, rather than replacing, the reference methods. Their calibration depends on the reference methods, their performance degrades when material composition drifts outside the calibration space, and specification conformity is defined contractually in terms of the reference procedures. The appropriate deployment is therefore rapid instrumental screening for process control with reference-method confirmation for conformity decisions and for disputes.

5. Discussion

The evaluation supports several conclusions about the design and use of the test battery. The first is that no single parameter is adequate for conformance assessment, and that the frequently encountered practice of trading on dry rubber content alone, with other parameters assessed only on dispute, exposes both parties to avoidable risk. The colloidal-stability parameters in particular have no proxy in the composition data, since two latices of identical total solids, dry rubber content, and alkalinity may differ substantially in mechanical stability depending on their maturation and spoilage history.

The second is that several parameters are informative principally in combination. The KOH number requires the VFA number for interpretation; ash requires dirt; Mooney viscosity requires knowledge of material age for non-constant-viscosity grades; and plasticity retention index requires initial plasticity, since the index is a ratio and a high ratio computed from a low initial value has different processing implications from the same ratio computed from a high initial value. Specification schemes that report parameters as independent pass or fail determinations discard this joint information.

The third is that the uncertainty structure of the battery is markedly uneven, and that quality management effort is frequently misallocated in consequence. The gravimetric and titrimetric determinations are well controlled and rarely the source of genuine disagreement. The functional tests, principally plasticity retention index and mechanical stability time, carry the largest uncertainty and simultaneously the greatest predictive value, which is an uncomfortable but unavoidable combination. Improvement effort directed at ageing oven qualification, stirrer maintenance, and end-point standardisation yields disproportionate return.

The fourth concerns the position of sampling within the measurement system. Because both latex concentrate and baled dry rubber are heterogeneous on the scale from which test portions are drawn, sampling error is often the dominant uncertainty component and is rarely quantified. Laboratories that report analytical repeatability without addressing sampling variance materially overstate the reliability of their conformity statements. Estimation of sampling variance through replicate independent sampling of the same consignment is straightforward and is recommended where conformity decisions have significant commercial consequence.

Finally, the industrial significance of the battery extends beyond acceptance decisions on individual consignments. Trend analysis across consignments from a given origin provides early warning of upstream changes: a downward alkalinity trend indicates deteriorating preservation practice;

rising VFA numbers indicate hygiene or transit problems; rising dirt indicates field collection practice changes; falling PRI may indicate changed drying conditions or clone composition. Used in this way, the test battery functions as a supplier development instrument rather than solely as a gatekeeping mechanism, and the value realised from the same testing expenditure is substantially greater.

A practical consideration in applying the latex battery concerns the sequence and timing of determinations after receipt. Volatile fatty acid number and mechanical stability time change measurably within days under warm ambient conditions, whereas total solids content, dry rubber content, and ash are effectively stable. Determinations of the labile parameters should therefore be scheduled immediately on receipt, with the stable parameters deferred if laboratory loading requires. Where disputes are anticipated, retained samples should be stored under defined conditions, preferably refrigerated in filled, sealed containers with minimal headspace, and the storage conditions should be recorded, since ammonia loss from partially filled containers alters alkalinity and secondary parameters within weeks.

The relationship between dry rubber content and the commercial basis of transactions merits explicit treatment because it is a frequent source of dispute. Latex concentrate is normally invoiced on dry rubber content, so a 0.2 percentage point disagreement on a 60 per cent nominal material represents approximately a 0.33 per cent commercial difference on the consignment value. Since this is comparable to the reproducibility of the determination between laboratories, contracts should specify the arbitration procedure, the accredited laboratory to be used, and whether the arbitration result replaces or is averaged with the party determinations. Contracts lacking such provisions generate disputes that the measurement science cannot resolve.

For dry rubber, a parallel commercial consideration arises from volatile matter. Because material is traded on gross mass, a consignment at 0.75 per cent volatile matter delivers measurably less rubber hydrocarbon than one at 0.25 per cent, though both conform to the 0.80 per cent limit. Some purchasers therefore apply a moisture adjustment clause. Where such clauses operate, the volatile matter determination acquires direct commercial weight and warrants correspondingly careful control, including verification that the oven method and hot-mill method give equivalent results on the material in question, since they may diverge for material containing volatile organic residues in addition to water.

Regarding the interpretation of mechanical stability time in relation to product type, requirements differ systematically across applications. Coagulant dipping for gloves requires latex that destabilises reliably on contact with the coagulant, and excessively high mechanical stability can produce incomplete or uneven deposition. Foam manufacture by the Dunlop process requires latex that withstands prolonged mechanical frothing and then gels reliably on addition of the gelling agent, a demanding combination of stability and controlled instability. Adhesive and binder applications are generally more tolerant. Purchasers should therefore specify a mechanical stability window rather than a minimum alone where the application is stability-sensitive.

An additional latex parameter not always included in routine batteries but of consequence for certain applications is the content of copper and manganese, determined under ISO 8053 and ISO 7780 respectively. Both are pro-oxidant transition metals that catalyse oxidative degradation of the polyisoprene and reduce the ageing performance of the vulcanisate. ISO 2004 specifies maxima of 8 mg/kg on total solids for each. Contamination arises principally from processing equipment and from certain agricultural inputs, and elevated values indicate a traceable upstream source that is usually correctable.

Colour index determination under ISO 4660 applies to light-colour grades and uses the Lovibond comparator to assign an index by visual matching of a moulded disc against standard glasses. The determination is inherently subjective, is affected by illuminant and observer, and exhibits poor reproducibility relative to instrumental colour measurement. Where colour is commercially significant, instrumental measurement in a defined colour space with specified illuminant and observer conditions provides substantially better agreement, though it is not the reference method under the specification.

Ageing oven qualification for the plasticity retention index is the single most consequential item of equipment control in the dry rubber battery. Qualification should establish the spatial temperature distribution across the loaded working volume at operating temperature, the recovery time after door opening, and the stability over the 30 min ageing period. Positions failing the uniformity requirement

should be physically blocked from use. Loading patterns validated during qualification should be documented and adhered to, since altering the number or arrangement of test pieces changes the thermal load and hence the recovery behaviour.

Finally, the relationship between the specification battery and end-product performance testing deserves clear statement. Conformance to ISO 2004 or ISO 2000 establishes that the raw material falls within an agreed range on the specified parameters; it does not guarantee performance in any particular formulation or process. Manufacturers with demanding applications commonly supplement specification testing with application-relevant evaluation, such as small-scale compounding and cure characterisation for dry rubber, or pilot dipping trials for latex. The specification battery should be understood as a necessary but not sufficient basis for material acceptance, and the additional evaluation appropriate to a given application is a matter for the manufacturer's own process knowledge.

6. Conclusion

This evaluation examined the critical conformance tests applied to ammonia-preserved natural rubber latex concentrate and to technically specified dry rubber, setting out for each test its principle, procedure, calculation basis, and interpretive significance. Four conclusions follow.

First, conformance cannot be established from any single parameter. The battery is structured so that compositional, contamination, and functional properties are separately assessed, and the colloidal-stability and oxidative-stability parameters in particular have no compositional proxy.

Second, several parameters are interpretable only in combination. The KOH number requires the volatile fatty acid number to distinguish benign maturation from bacterial spoilage; ash requires dirt to distinguish endogenous minerals from soil contamination; and the plasticity retention index requires the initial plasticity from which it is derived.

Third, the uncertainty structure of the battery is uneven. Gravimetric and titrimetric determinations are well controlled, whereas the mechanical stability time and the plasticity retention index carry substantially larger uncertainty while simultaneously offering the greatest predictive value for processing behaviour. Quality assurance effort is best concentrated on ageing oven qualification, stirrer condition, solids adjustment accuracy, and end-point standardisation.

Fourth, sampling frequently dominates the total uncertainty budget for these heterogeneous materials, and analytical repeatability reported without regard to sampling variance overstates the reliability of conformity statements.

Used beyond individual acceptance decisions, trend analysis across consignments converts the same testing expenditure into a supplier development instrument capable of identifying upstream changes in preservation practice, field hygiene, and processing conditions before they produce non-conforming material.

References

1. ISO 35:2004, Natural rubber latex concentrate — Determination of mechanical stability, International Organization for Standardization, Geneva.
2. ISO 123:2001, Rubber latex — Sampling, International Organization for Standardization, Geneva.
3. ISO 124:2014, Latex, rubber — Determination of total solids content, International Organization for Standardization, Geneva.
4. ISO 125:2011, Natural rubber latex concentrate — Determination of alkalinity, International Organization for Standardization, Geneva.
5. ISO 126:2005, Natural rubber latex concentrate — Determination of dry rubber content, International Organization for Standardization, Geneva.
6. ISO 127:2012, Rubber, natural latex concentrate — Determination of KOH number, International Organization for Standardization, Geneva.
7. ISO 247:2006, Rubber — Determination of ash, International Organization for Standardization, Geneva.

8. ISO 248-1:2011, Rubber, raw — Determination of volatile-matter content — Part 1: Hot-mill method and oven method, International Organization for Standardization, Geneva.
9. ISO 249:2016, Rubber, raw natural — Determination of dirt content, International Organization for Standardization, Geneva.
10. ISO 506:1992, Rubber latex, natural, concentrate — Determination of volatile fatty acid number, International Organization for Standardization, Geneva.
11. ISO 706:2004, Rubber latex — Determination of coagulum content (sieve residue), International Organization for Standardization, Geneva.
12. ISO 1656:2014, Rubber, raw natural, and rubber latex, natural — Determination of nitrogen content, International Organization for Standardization, Geneva.
13. ISO 1795:2017, Rubber, raw natural and raw synthetic — Sampling and further preparative procedures, International Organization for Standardization, Geneva.
14. ISO 2000:2014, Rubber, raw natural — Guidelines for the specification of technically specified rubber (TSR), International Organization for Standardization, Geneva.
15. ISO 2004:2017, Natural rubber latex concentrate — Centrifuged or creamed, ammonia-preserved types — Specifications, International Organization for Standardization, Geneva.
16. ISO 2005:2016, Natural rubber latex concentrate — Determination of sludge content, International Organization for Standardization, Geneva.
17. ISO 2007:2019, Rubber, unvulcanized — Determination of plasticity — Rapid-plastimeter method, International Organization for Standardization, Geneva.
18. ISO 2930:2017, Rubber, raw natural — Determination of plasticity retention index (PRI), International Organization for Standardization, Geneva.
19. ISO 289-1:2015, Rubber, unvulcanized — Determinations using a shearing-disc viscometer — Part 1: Determination of Mooney viscosity, International Organization for Standardization, Geneva.
20. ISO 4660:2011, Rubber, raw natural — Colour index test, International Organization for Standardization, Geneva.
21. ISO 5725-2:2019, Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method, International Organization for Standardization, Geneva.
22. ISO/IEC 17025:2017, General requirements for the competence of testing and calibration laboratories, International Organization for Standardization, Geneva.
23. ASTM D1076-21, Standard Specification for Rubber — Concentrated, Ammonia Preserved, Creamed, and Centrifuged Natural Latex, ASTM International, West Conshohocken, PA.
24. ASTM D1278-21, Standard Test Methods for Rubber from Natural Sources — Chemical Analysis, ASTM International, West Conshohocken, PA.
25. ASTM D3157-21, Standard Test Methods for Rubber from Synthetic Sources — Chemical Analysis, ASTM International, West Conshohocken, PA.
26. D. C. Blackley, Polymer Latexes: Science and Technology, 2nd ed., Vol. 2: Types of Latexes, Chapman & Hall, London, 1997.
27. A. D. Roberts (Ed.), Natural Rubber Science and Technology, Oxford University Press, Oxford, 1988.
28. J. E. Mark, B. Erman, and C. M. Roland (Eds.), The Science and Technology of Rubber, 4th ed., Academic Press, Oxford, 2013.
29. Y. Tanaka, 'Structural characterization of natural polyisoprenes: Solve the mystery of natural rubber based on structural study,' Rubber Chemistry and Technology, vol. 74, no. 3, pp. 355–375, 2001.

30. K. Nawamawat, J. T. Sakdapipanich, C. C. Ho, Y. Ma, J. Song, and J. G. Vancso, 'Surface nanostructure of Hevea brasiliensis natural rubber latex particles,' *Colloids and Surfaces A*, vol. 390, no. 1–3, pp. 157–166, 2011.
31. E. Yip and P. Cacioli, 'The manufacture of gloves from natural rubber latex,' *Journal of Allergy and Clinical Immunology*, vol. 110, no. 2, pp. S3–S14, 2002.
32. S. Kawahara, T. Kakubo, J. T. Sakdapipanich, Y. Isono, and Y. Tanaka, 'Characterization of fatty acids linked to natural rubber — role of linked fatty acids on crystallization of the rubber,' *Polymer*, vol. 41, no. 20, pp. 7483–7488, 2000.
33. International Rubber Study Group, *Rubber Statistical Bulletin*, Singapore, various issues.
34. Malaysian Rubber Board, *SMR Bulletin: Standard Malaysian Rubber Scheme specifications and test procedures*, Kuala Lumpur.
35. Rubber Research Institute of India, *Handbook of Natural Rubber Production in India*, Kottayam.